

Hall tunneling of vortices in superclean superconductors

D.A.Gorokhov* and G. Blatter *

Abstract

We discuss the main features of Hall tunneling of pancake vortices in superclean high- T_c superconductors. The general formalism for the calculation of the lifetime of a vortex pinned in a metastable configuration is described. The results are applied to the problem of quantum tunneling of a pancake vortex from a columnar defect in the limit of a small driving current.

An external magnetic field penetrates a type-II superconductor in the form of vortices — flux tubes enclosing a quantum $\Phi_0 = \pi\hbar c/e$ of magnetic flux. The new class of high temperature superconductors exhibits a large variety of vortex related phenomena, which can be tuned by specific material parameters¹, e.g., the material anisotropy and the macroscopic and microscopic amount of disorder, the former determining vortex pinning, whereas the latter is responsible for the vortex dynamics. Here we are interested in highly anisotropic (layered) clean material. A single vortex then can be represented as a chain of pancake vortices. The (low frequency) vortex equation of motion takes the form

$$\frac{\Phi_0}{c} \mathbf{j} \wedge \mathbf{n} - \nabla U_{pin} = \eta \mathbf{v} + m \dot{\mathbf{v}} + \alpha \mathbf{v} \wedge \mathbf{n}, \quad (1)$$

* *Theoretische Physik, ETH-Hönggerberg, CH-8093 Zürich, Switzerland;* e-mail: gorokhov@itp.phys.ethz.ch

where the dynamical forces (the Hall term $\alpha \mathbf{v} \wedge \mathbf{n}$, the massive term $(m\dot{\mathbf{v}})$, and the dissipative term $(-\eta \mathbf{v})$) are balanced by the Lorentz and pinning forces. In this paper we consider pancake vortices parallel to the c -axis of a layered superconductor.

Usually one can neglect the massive term. The ratio of the dynamical coefficients α and η can be estimated as $\alpha/\eta \simeq (\Delta/\epsilon_F)(l/\xi)$, with Δ the gap, ϵ_F the Fermi energy, l the electron mean free path, and ξ the (ab -plane) coherence length. Typically, in high- T_c superconductors $\Delta/\epsilon_F \simeq 1/10$ – $1/20$, $l \simeq 700$ Å, and $\xi \simeq 20$ Å, i.e., we obtain $\alpha/\eta \simeq 1$; in conventional superconductors $\alpha/\eta \ll 1$ due to the small ratio Δ/ϵ_F , as typically $\Delta \sim 10$ K and $\epsilon_F \sim 10^4$ K). Indeed, recent experiments suggest that the regime $\alpha/\eta \gtrsim 1$ can be realized. In this situation, we can neglect the dissipative term in the vortex equation of motion (1) and describe the dynamics of the pancake vortex with the Hall term alone. As a result, the problem becomes equivalent to that of a particle moving in a strong magnetic field.

The Lagrangian describing a pancake vortex in the presence of a potential $U(x, y)$ produced by pinning and Lorentz forces can be written in the form

$$L = \alpha \dot{x}y - U(x, y). \quad (2)$$

and the associated equations of motion read

$$\alpha \dot{x} = \frac{\partial U(x, y)}{\partial y}, \quad (3)$$

$$\alpha \dot{y} = -\frac{\partial U(x, y)}{\partial x}. \quad (4)$$

These equations of motion are equivalent to those produced by the 1D Hamiltonian $H(x, p) = U(x, p/\alpha)$, i.e., our problem is effectively one dimensional². We consider a pinning potential of the form $U_{pin} = U(\sqrt{x^2 + y^2})$ producing a stable trapped vortex state (such pinning centers can be created by heavy ion irradiation). For a nonzero external driving current $\mathbf{j}$ this state becomes metastable, resulting in a finite lifetime for the trapped pancake vortex. At low temperatures only tunneling from the ground state is relevant, whereas at

higher temperatures thermal effects become important. In this note we study the vortex depinning at arbitrary temperatures. The problem of Hall tunneling of vortices in high- T_c superconductors has been studied for various geometries and for different external currents, see Refs. 3-9. Below we follow the analysis of Ref. 9 (see also Ref. 10).

The (real time) Lagrangian (2) produces the Euclidean action (we carry out the substitution $S = \int L dt \rightarrow -iS$ and $t \rightarrow -i\tau$)

$$S_{\text{Eucl}} = \int_{-\hbar/2T}^{+\hbar/2T} \left[-i\alpha \dot{x}y + U_0 \left(\sqrt{x^2 + y^2} \right) \right] d\tau. \quad (5)$$

In general, the imaginary unit appearing in the Euclidean action renders the saddle-point solution complex. However, in the present case we can reduce the complex problem to a real one¹ via the additional transformation $y \rightarrow iy$, replacing $U_0 \left(\sqrt{x^2 + y^2} \right)$ by $U_0 \left(\sqrt{x^2 - y^2} \right)$. After this transformation the Lagrangian exhibits a saddle-point solution and we can calculate the decay rate following the standard technique. The effective tunneling problem is described by the Euclidean action

$$S_{\text{Eucl}}[x(\tau), y(\tau)] = \int_{-\hbar/2T}^{+\hbar/2T} [\alpha \dot{x}y + U_0(\sqrt{x^2 - y^2}) - Fx] d\tau. \quad (6)$$




Fig.1 Quasiclassical (x, y) -trajectories corresponding to the tunneling of the vortex. The Euclidean action corresponding to the zero temperature trajectory (thick line) is equal to the encircled area. The thick dotted line marks a finite temperature bounce trajectory..

The bounce trajectories are given by the condition $U_0 \left(\sqrt{x^2 - y^2} \right) - Fx = \text{Const}$ and are shown in Fig. 1. The problem studied here exhibits the interesting feature of geometric quantization: the action is proportional to the area encircled by the pancake vortex during its motion in imaginary time. At zero temperature $U_0 \left(\sqrt{x^2 - y^2} \right) - Fx = 0$ and $S_{\text{Eucl}} = \int_{-\infty}^{+\infty} \alpha \dot{x} y d\tau = \alpha \oint x dy$. The Euclidean action at finite temperatures can be calculated using the following technique: The imaginary time trajectory at a finite energy E is given by the equation $U_0 \left(\sqrt{x^2 - y^2} \right) - Fx = E$. The trajectories are distributed with the Boltzmann weight, i.e, we have to find the trajectory for which $-S(E)/\hbar - E/T$ takes a maximal value. In the limit of small external currents the problem can be solved analytically in the whole temperature range (see Ref. 9). The Euclidean action (which determines the decay rate Γ to exponential accuracy, $\Gamma \sim \exp(-S_{\text{Eucl}}/\hbar)$) can be written in the form

$$S_{\text{Eucl}} = \begin{cases} \alpha \left(\frac{U_0}{F} \right)^2, & T < \frac{\hbar F^2}{2\alpha U_0} \equiv T_1, \\ \frac{\hbar U_0}{T} - \frac{\hbar^2 F^2}{4\alpha T^2}, & T_1 < T, \end{cases} \quad (7)$$

where U_0 is the depth of the pinning potential and F denotes the external force acting on the pancake vortex. The function $S_{\text{Eucl}}(T)$ is a constant below the temperature T_1 , whereas above T_1 thermal corrections become relevant. We investigated in detail the crossover from the thermal assisted quantum regime to the region of purely thermal activation. For the pinning potential exhibiting a large-distance asymptotic behavior of the form $U(r) \rightarrow U_0 - B/r^2$, the transition is second-order like with the crossover temperature given by the formula

$$T_c = \frac{\sqrt{3}}{2^{4/3}} \frac{\hbar F^{4/3}}{\alpha B^{1/3}}. \quad (8)$$

For $T > T_c$ the escape process is purely thermal with $S_{\text{Eucl}} = \hbar U_0/T$, i.e. the decay is due to thermal activation alone. The evolution of the Euclidean action with increasing temperature is sketched in Fig. 2.




Fig.2 Euclidean action as a function of temperature. At $T < T_1 = \hbar F^2 / 2\alpha U_0$, S_{Eucl} is a constant up to exponentially small corrections. In the regime $T > T_1$ the Euclidean action begins to decrease, see Eq. (7). The temperature $T = T_c$ (see Eq. (8)) marks the second-order like transition from quantum to classical behavior.

In conclusion, we have briefly summarized the Hall-creep of pancake vortices relevant in clean high-temperature superconductors.

REFERENCES

- ¹ For a review see G. Blatter *et al.*, *Rev. Mod. Phys.* **66**, 1125 (1994).
- ² G. E. Volovik, *Pis'ma Zh. Eksp. Teor. Fiz.* **15**, 116 (1972) [*JETP Lett.* **15**, 81 (1972)].
- ³ M. V. Feigel'man *et al.*, *Pis'ma Zh. Eksp. Teor. Fiz.* **57**, 699 (1993) [*JETP Lett.* **57**, 711 (1993)].
- ⁴ P. Ao and D. J. Thouless, *Phys. Rev. Lett.* **72**, 132 (1994).
- ⁵ M. J. Stephen, *Phys. Rev. Lett* **72**, 1534 (1994).
- ⁶ E. M. Chudnovsky *et al.*, *Phys Rev. B* **51**, 1181 (1995).
- ⁷ E. B. Sonin and B. Horovitz, *Phys. Rev. B* **51**, 6526 (1995).
- ⁸ C. Morais-Smith *et al.*, *Phys. Rev. B* **54**, 784 (1996).
- ⁹ D. A. Gorokhov and G. Blatter, *Phys. Rev. B* **57**, 3586 (1998); D. A. Gorokhov and G. Blatter *Phys. Rev. B* **57**, 3577 (1998).
- ¹⁰ D. A. Gorokhov and G. Blatter, *Phys. Rev. B* **56**, 3130 (1997); D. A. Gorokhov and G. Blatter, *Phys. Rev. B* **58**, 5486 (1998).